

## Medina Velour

<b>Construction</b>	1/10 CUT Velours, plain
<b>Fire resistance</b>	EN ISO 9239-1 Cfls1
<b>Manufacturing process</b>	Tufted
<b>Fastness to light</b>	ISO 105-B02 7
<b>Pile material</b>	SOLUTION DYED
<b>Rubbing fastness</b>	EN ISO 105-X12 4
<b>Primary backing</b>	Synthetic
<b>Colour fastness to water</b>	EN ISO 105-E01 4
<b>Secondary backing</b>	Modified bitumen enhanced with a thermoplastic elastomer reinforced with a glass fibre fleece
<b>Thermal resistance</b>	ISO 8302 0,05 qm K/W
<b>Rug</b>	covered with a 100% PES fleece
<b>Total weight</b>	Ca. 4.750 g/m <sup>2</sup>
<b>Impact noise rating</b>	Lw ISO 140-8 25 dB
<b>Pile weight</b>	Ca. 750 g/m <sup>2</sup>
<b>Sound absorption</b>	ISO 354 Hz 125 250 500 1000 2000 4000 S 0.02 0.02 0.08 0.26 0.31 0,37
<b>Pile above backing</b>	Ca. 500 g/m <sup>2</sup>
<b>Permanent Antistatic</b>	PrEN 1815 <2KV
<b>Total height</b>	Ca. 7,5 mm
<b>Transversal resistance</b>	ISO/DIS 10965 109 Ohm
<b>Size</b>	50 x 50cm - 60 x 60 cm on request
<b>Pile density</b>	Ca. 0,130 g/cm <sup>3</sup>
<b>Packing box</b>	5 m <sup>2</sup>
<b>Pallet</b>	20 boxes
<b>Tuft density</b>	Ca. 158.000/ m <sup>2</sup>
<b>Number of colours</b>	24
<b>Gut.-Nr</b>	<b>EN 1307: 33 LC 2</b>
<b>Dimensional Stability</b>	EN 986 Max. - 0.2%

Shades may vary from batch to batch and should be checked before installation. Bürofloor carpet tiles must be installed according to our instructions and in accordance with the relevant British Standards.

Regular vacuum cleaning is recommended, spills and stains must be removed as part of a comprehensive maintenance plan.

We reserve the right to alter technical specification without prior notice.